

JP 7/258460

DIALOG(R)File 351:Derwent WPI
(c) 2006 Thomson Derwent. All rts. reserv.

010478865

WPI Acc No: 1995-380186/*199549*

**Resin compsn. for mouldings having metallic tone - obtained by
compounding metal-coated glass flakes and thermoplastic resin contg.
fluorescent dye and/or pigment**

Patent Assignee: TEIJIN KASEI LTD (TEIQ)

Number of Countries: 001 Number of Patents: 002

Patent Family:

Patent No	Kind	Date	Applicat No	Kind	Date	Week
JP 7258460	A	19951009	JP 9450251	A	19940322	199549 B
JP 3573481	B2	20041006	JP 9450251	A	19940322	200465

Priority Applications (No Type Date): JP 9450251 A 19940322

Patent Details:

Patent No	Kind	Lan	Pg	Main IPC	Filing Notes
JP 7258460	A		3	C08K-005/00	
JP 3573481	B2		5	C08L-101/00	Previous Publ. patent JP 7258460

Abstract (Basic): JP 7258460 A

A resin compsn. is obtd. by compounding 0.01-10 pts.wt. of glass flakes coated with a metal, and having an average particle size of 0.01-3 μ m, and an average thickness of 1-30 μ m, with (A) 100 pts. wt. a light transmitting thermoplastic resin contg (B) a fluorescent dye and/or fluorescent pigment. (A) is polycarbonate, acrylic resin, polystyrene or AS resin. (B) is of perylene type. The amt. of (B) is 0.001-5.0 wt.% based on the combined amt. of (A) and (B).

ADVANTAGE - The resin compsn. provides mouldings having a fancy metallic tone.

Dwg.0/0

Derwent Class: A60

International Patent Class (Main): C08K-005/00; C08L-101/00

International Patent Class (Additional): C08K-003/08; C08K-009/02
